



# MAGNAVIS # 8A Red

## DRY MAGNETIC PARTICLES



### General Description

Magnavis # 8A Red is ready to use, free flowing general purpose, dry method, colour contrast magnetic powders. These powders are used to locate surface and slightly subsurface discontinuities in ferrous structures.

# 8A Red is a red coloured powder, which produces sharp colour contrast indications on most surfaces and colored backgrounds.

### Applications

Typical applications include welds, large forgings and castings, and where rough surfaces are encountered

### Composition

The dry magnetic powders are composed of selected magnetic powders and pigments.

### Typical Properties (not a specification)

Property	# 8A Red
Form	Free flowing powder
Colour	Dark Red
Mean Particle size	80 microns
SAE sensitivity	7
Upper temperature limit*	315 °C

\*Temperature limits are not intended to imply that the material will not form magnetic particle indications above the specified temperatures. However, particles at elevated temperatures for a period of time may be altered in colour, sintered together or emit smoke. Particles heated to 480°C or passed through a flame will smoulder or spark.

Like all Magnaflux materials Magnavis #8A Red dry magnetic powders are closely controlled to provide unique batch to batch consistency and uniformity to assure optimum process control and inspection reliability.

### Benefits

- ✓ Ready to use
- ✓ Coloured powder to suit contrast on most surfaces and coloured backgrounds



## Method of Use

Our dry method, non-fluorescent magnetic particles may be dispensed by the Powder Spray Bulb, a plastic squeeze bottle, or a powder blower.

The powders must be applied while the magnetising current is on. If there is considerable background build-up, the excess material can be gently blown off while the current is flowing. Should the material being tested have a high retentivity, surface discontinuities can be detected after the current shot.

## Specification Compliance

Specification	# 8A Red
AMS 3040	✓
ASME B & PV Code, Sec V	✓
ASTM E-709	✓
ASTM E-1444	✓
BS EN ISO 9934-2	✓

## Availability

# 8A Red is available in 1 Kg containers, part number F03002

## Health and Safety

- Safety Data Sheets for this product are available on request from your Magnaflux distributor or via the Magnaflux website ([www.in.magnaflux.com](http://www.in.magnaflux.com)).
- Read the relevant Safety Data Sheets before use.

**ITW INDIA PRIVATE LIMITED,**  
 Plot No: 51, 52, 207 & 208, Phase – 2,  
 IDA, TSIIIC, Pashamylaram,  
 Sangareddy Dist.-502307,  
 Telangana, India

Tel: +91 8455 224710 Fax: +91 8455 224709  
 Email: [magnafluxinfo@magnafluxindia.com](mailto:magnafluxinfo@magnafluxindia.com)  
[www.in.magnaflux.com](http://www.in.magnaflux.com)

F/MKTG/198 /0 Rev 11/2018

